



### MINIMUM STANDARDS

STANDARD DIMENSIONS	ITEM	DESCRIPTION	ARTERIAL	COMM.&IND.	COLLECTOR	LOCAL NO PARKING	LOCAL WITH PARKING	LOCAL NO PARKING
I	RIGHT-OF-WAY	*	60	60	50	60	50	50
II	B\B CURB	*	41	36	30	36	24	24
III	SIDEWALK WIDTH	6'	5'	6'	5'	5'	5'	5'
IV	CURB LAWN WIDTH	*	4.5'	5'	4'	6'	7'	7'
ASPHALT BASE AGGREGATE BASE	V	ITEM 448	1-1/4"	1-1/4"	1-1/4"	1-1/4"	1-1/4"	1-1/4"
	VI	ITEM 448	1-3/4"	1-3/4"	2-3/4"	2-1/4"	2-3/4"	2-3/4"
	VII	ITEM 301	7"	3"	—	—	—	—
	VIII	ITEM 304	6"	9"	9"	9"	9"	9"
ASPHALT BASE	V	ITEM 448	1-1/4"	1"	1"	1"	1"	1"
	VI	ITEM 448	1-3/4"	2"	2"	2"	2"	2"
	VII	ITEM 301	8"	6"	5"	4"	5"	5"

\* SEE DESIGN CRITERIA AND CITY ENGINEER

### NOTES

- A. ALL WORK TO CONFORM TO ODOT CONSTRUCTION AND MATERIAL SPECIFICATIONS LATEST REVISION UNLESS OTHERWISE SPECIFIED.
- B. ITEM 407 TACK COAT, SHALL BE REQUIRED WHEN 5 DAYS HAVE ELAPSED BETWEEN BITUMINOUS PAVEMENT LIFTS UNLESS OTHERWISE SPECIFIED BY THE ENGINEER. APPLICATION RATE IS 0.10 GALLON PER SQUARE YARD.
- C. ALL BUTT JOINTS SHALL BE SEALED WITH PG 64-22 WITHIN 24 HOURS AFTER PLACEMENT OF ITEM 448.
- D. STANDARD DIMENSIONS FOR (II) B\B CURB AND (IV) APRON WIDTH ASSUME PARKING ON BOTH SIDES.
- E. IN AREAS WITH HIGH POTENTIAL OF PUSHING, SHOVING OR HEAVING, USE ITEM 448 ASPHALT CONCRETE SURFACE COURSE TYPE 1 H, PG. 70-22. IN SMALL QUANTITY AREAS USE TYPE 1, PG 64-22 WITH GILSONITE ADDITIVE.
- F. CONCRETE PAVEMENT WILL BE CONSIDERED UPON SUBMITTAL OF TYPICAL SECTION DESIGN.



CITY OF  
SIDNEY

## TYPICAL SECTIONS AND ASPHALT PAVEMENT COMPOSITION

REVISIONS: 06-25-07 07-22-13	DATE APPROVED: 06/03/2020
PAGE No. 300-2	